

## SECTION 1 - IDENTIFICATION

**COMPANY ADDRESS:**  
 The Virtual Foundry, Inc  
 1471 US HWY 51  
 Stoughton, WI 53589  
 USA

**PRODUCT NAME:** Inconel® 718 Filamet™

## SECTION 2 - TYPICAL MATERIAL PROPERTIES

Physical Properties	Unit	Value
Density	g/cc	3.23
Humidity Absorption	%	No information available
Tensile Strength	MPa	No information available
Tensile Elongation	%	No information available
Flexural Strength	MPa	No information available
Flexural Modulus	GPa	No information available
Izod Impact Strength	kJ/m <sup>2</sup>	No information available

## SECTION 5 - FILAMENT SPECIFICATIONS

Nominal Diameter	Diameter Tolerance	Ovality
1.75mm	± 0.05mm	≥ 95%
2.85mm	± 0.05mm	≥ 95%
Net Filament Weight	Metal Content	
1000/500 grams	82.0 - 85.0%	

## SECTION 6 - GUIDELINES FOR PRINTING

<b>Advised Printing Temperature</b>	190-230°C (374 – 446°F)
<b>Advised Build Plate Temperature</b>	40-65°C (104 – 149°F) (Optional) 65°C (149°F) is recommended for glass/G10 build plates
<b>Build Plate Surface Type</b>	Powder coated spring steel, glass, G10, blue painter's tape
<b>Build Plate Preparation</b>	Powder Coated Spring Steel: No preparation required Glass/G10: Clean with IPA, print at 65°C (149°F) PEI/PC/Fiberglass/Acrylic/Other: Blue painter's tape

Print Cooling

Recommended for small details/intricate parts

Advised Printing Speed

60-80mm/sec

Nozzle Size/Type

0.6mm Hardened Steel

## SECTION 10 - ADDITIONAL INFORMATION

This filament is abrasive and will wear standard brass nozzles fast. The Virtual Foundry, Inc recommends a hardened steel nozzle. Gem tipped, stainless steel, titanium and tungsten nozzles have been tested and found to wear quickly.

Sintering Temperature: 1260°C (2300°F)

Instructions: <https://thevirtualfoundry.com/debind-sinter/>

**DISCLAIMER:** The information provided in this TDS is correct to the best of The Virtual Foundry, Inc's knowledge. The Virtual Foundry, Inc makes no warranty, express or implied, regarding the accuracy of the data or the results obtained from the use of this product. Nothing herein may be construed as recommending any practice or any product in violation of any law or regulations. The information given is provided as a guidance for good use, handling and processing and is not to be considered as a quality specification. The user is solely responsible for determining the suitability of any material or product for a specific purpose and for adopting any appropriate safety precautions. The information only relates to the specific product and the material properties.

REVISED DATE:

April 2024