

## SECTION 1 - IDENTIFICATION

**COMPANY ADDRESS:**  
 The Virtual Foundry, Inc  
 1471 US HWY 51  
 Stoughton, WI 53589  
 USA

**PRODUCT NAME:** Zirconium Silicate Filamet™

## SECTION 2 - TYPICAL MATERIAL PROPERTIES

Physical Properties	Unit	Value
Density	g/cc	2.11
Ceramic Content	%	64.0 - 69.0

## SECTION 3 - FILAMENT SPECIFICATIONS

Nominal Diameter	Diameter Tolerance	Ovality	Net Filament Weight
1.75mm	± 0.05mm	≥ 95%	1000 / 500 / 250 grams
2.85mm	± 0.05mm	≥ 95%	1000 / 500 / 250 grams
Pellets	-	-	1000 grams

## SECTION 4 - GUIDELINES FOR PRINTING

<b>Advised Printing Temperature</b>	190 - 230°C (374 - 446°F) For high speed printers: 235 - 250°C (455 - 482°F)
<b>Advised Build Plate Temperature</b>	40 - 65°C (104 - 149°F) (Optional) 65°C (149°F) is recommended for glass/G10 build plates
<b>Build Plate Surface Type</b>	Powder coated spring steel, glass, G10, blue painter's tape
<b>Build Plate Preparation</b>	Powder Coated Spring Steel: No preparation required Glass/G10: Clean with IPA, print at 65°C (149°F) PEI/PC/Fiberglass/Acrylic/Other: Blue painter's tape
<b>Print Cooling</b>	Recommended for small details/intricate parts
<b>Advised Printing Speed</b>	60 - 80mm/sec For high speed printers: 120 - 130mm/sec
<b>Advised Flow Rate</b>	120 - 135%
<b>Nozzle Size/Type</b>	0.6mm Hardened Steel

#### SECTION 5 - ADDITIONAL INFORMATION

This filament is abrasive and will wear standard brass nozzles fast. The Virtual Foundry, Inc recommends a hardened steel nozzle. Gem tipped, stainless steel, titanium and tungsten nozzles have been tested and found to wear quickly.

**Sintering Temperature:** 1500°C (2732°F)                      Untested

**DISCLAIMER:** The information provided in this TDS is correct to the best of The Virtual Foundry, Inc's knowledge. The Virtual Foundry, Inc makes no warranty, express or implied, regarding the accuracy of the data or the results obtained from the use of this product. Nothing herein may be construed as recommending any practice or any product in violation of any law or regulations. The information given is provided as a guidance for good use, handling and processing and is not to be considered as a quality specification. The user is solely responsible for determining the suitability of any material or product for a specific purpose and for adopting any appropriate safety precautions. The information only relates to the specific product and the material properties.

**REVISED DATE:**    March 2025